

SOLUTION WELDING COMPOUND

For converting of PVC-P-membranes

Properties:

Basis:	soluble synthetic resin
Density (20°C):	0.9 g/cm ³
Viscosity:	thin fluid
Colour:	colourless, transparent

Storage:

Containers must be kept sealed. Store in a cool, dry place in well-sealed containers. Only store out-doors in explosion-proof rooms (+15°C to +25°C). Protect against air/oxygen ingress (formation of peroxide). Store locked away or only accessible to specialist personnel or persons authorised by the same.

Application:

- Solution welding compound is one-sided applied thickly by a soft brush or by effusion
- Both components have to be pressed on each other, so that a slight bead appears at the edges of the overlaps
- If destined areas are dried too much, procedure can be repeated
- Pressing on and fixing for 1–3 min
- Convenient processing temperature: 18–20 °C, do not apply at temp. below 5 °C
- Storage has to be cool and sealed

Safety:

Reaction to fire:	flammable
Labelling:	harmful

See information and instruction in the Material Safety Data Sheet

All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products at time of delivery. The customer/installer is responsible for the proper use and application of the product.

 ELBTAL PLASTICS

ELBTAL PLASTICS GmbH & Co. KG
Grenzstraße 9, D-01640 Coswig
GERMANY
Tel. +49 (0) 3523 5330 0
Fax. +49 (0) 3523 5330 220
www.elbtal-plastics.de